



OAK CHARDIN HERITAGE COLLECTION 190 X 18 / 4 X 1900MM

ENGINEERED PRODUCT SPECIFICATION DATASHEET

Product code D1213011	PRODUCT DESIGN	INFORMATION
Species European oak (Quercus Petraea)	Board Size	190 x 18 x 1900mm
Floor Type Multi-layer European oak Construction Engineered Top Layer 4mm Surface finish Brushed & matt varnished / lacquered Treatment Black, light brushed, light handscraped Profile As per drawing Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g., european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature bands within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Product code	D1213011
Construction Engineered Top Layer 4mm Surface finish Brushed & matt varnished / lacquered Treatment Black, light brushed, light handscraped Profile As per drawing Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Species	European oak (Quercus Petraea)
Top Layer 4mm Surface finish Brushed & matt varnished / lacquered Treatment Black, light brushed, light handscraped Profile As per drawing Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Floor Type	Multi-layer European oak
Surface finish Brushed & matt varnished / lacquered Treatment Black, light brushed, light handscraped Profile As per drawing Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board width +/-0.3mm Bow (length) (max) 10mm per linear metre	Construction	Engineered
Treatment Black, light brushed, light handscraped Profile As per drawing Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Top Layer	4mm
Profile As per drawing Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board width 10mm per linear metre	Surface finish	Brushed & matt varnished / lacquered
Box quantity 6 boards per pack (one nested row per pack) Pack size 2.166m² GRADING CRITERIA INFORMATION Grade Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Treatment	Black, light brushed, light handscraped
Pack size 2.166m² INFORMATION Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness Bow (length) (max) 10mm per linear metre	Profile	As per drawing
GRADING CRITERIA INFORMATION Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness Bow (length) (max) 10mm per linear metre	Box quantity	6 boards per pack (one nested row per pack)
Universal Grading: Contains a mixture of prime, nature and rustic/character grading. Different species will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Pack size	2.166m ²
will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber however may vary between boards and batches. Filler Allowed (All defects will be filled) Putty colour Black Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre		
Putty colourBlackMoisture content8-10%Gloss level10% (+/-5%)PlywoodPoplar / Eucalyptus plywoodBevelMicro bevel on all 4 sidesBoard length+/-2.0mmBoard width+/-0.5mmBoard thickness+/-0.3mmBow (length) (max)10mm per linear metre	Grade	will have different characteristics e.g. european oak grading tends to include it's fair share of knotting so there will be a more limited amount of prime/nature boards within universal grading. The boards will contain both heartwood and sapwood and have a degree of natural colour variation as a result. Sapwood of up to 30% of the face area is allowable. Knots are filled to match the natural timber
Moisture content 8-10% Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Filler	Allowed (All defects will be filled)
Gloss level 10% (+/-5%) Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Putty colour	Black
Plywood Poplar / Eucalyptus plywood Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Moisture content	8-10%
Bevel Micro bevel on all 4 sides Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Gloss level	10% (+/-5%)
Board length +/-2.0mm Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Plywood	Poplar / Eucalyptus plywood
Board width +/-0.5mm Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Bevel	Micro bevel on all 4 sides
Board thickness +/-0.3mm Bow (length) (max) 10mm per linear metre	Board length	+/-2.0mm
Bow (length) (max) 10mm per linear metre	Board width	+/-0.5mm
<u> </u>	Board thickness	+/-0.3mm
Weight 600kg p/m³	Bow (length) (max)	10mm per linear metre
	Weight	600kg p/m³



TECHNICAL	INFORMATION
Thermal conductivity	$\lambda = 0.17 \text{ W/mk}$
Thermal insualation value	$R = 0.115 \text{ m}^2 \text{ k/w}$
Class of reaction to fire	Dfl - S1
Brinnell hardness	Average HB 3.7
European standard	EN 14342:2005 wood flooring , EN 12524:2000 building materials
Formaldehyde emission	E1
CE marking / DOP	Available on request with our office or can be downloaded on www.wrg.ie.
EUTR	Responsibly sourced under EUTR regulations

INSTALLATION & STORAGE	INFORMATION
Installation	Floating / glue down or nail down installation. Please refer to the Whiteriver installation instructions included in each carton. Also available on www.wrg.ie
Warranty	20 year structural warranty
Usage	Indoor use only. Suitable for use over underfloor heating. Hot water systems only
Storage	Store flat & on a stable surface. Place product in the room at least 72 hours before installation to allow for acclimatisation
Air humidity	40 - 60%

FLOOR CARE & MAINTENANCE

Room Conditions:

Timber likes pleasant room conditions similar to humans: A room temperature of 20° and humidity of about 50%. The recommended range for timber flooring should be 18-22° and humidity 40-60%. A humidity controller may be required. All rooms which have timber flooring should ideally be maintained at the above. For underfloor heating the surface temperature of the wood surface should not exceed 25°celsius.

Protecting your floor:

To preserve quality and beauty of your floor we recommend you use protective pads and caster cups under chairs and furniture legs. If there is a door leading outside from the room where you have installed your hardwood flooring, use a door mat to catch the dirt and absorb the humidity. Never use a rubber matt, with styrofoam or plastic backing.

If you must move heavy pieces of furniture (e.g. refrigerator, piano, etc.), never slide them directly over the flooring. Instead, place a piece of carpet facedown between the legs and the flooring and pull the carpet to move the furniture.

The floor should be monitored every 6-12 months to inspect the conditions of the surface.

For further information please refer to the Floor Care and Maintenance manual included in the pack or alternatively visit www.wrq.ie

INSTALLATION & WARRANTY

All Whiteriver floors must be installed by a professional approved installer who has the necessary skills and will take each site circumstance into consideration. Our warranty is only valid on floors which have been installed by an approved flooring installer to BS8201. All floors must be installed as per our installation instructions. (Available on www.wrg.ie)











The grading image used in this datasheet is intended only as a guide of what the final product may look like. No rights can be taken from it. This technical data sheet was developed by Whiteriver Group, Cluide, Dunleer, Co Louth, Ireland, A92 V8YN. At the time of issuing this datasheet, all information is correctly stated. The company reserves the right to update or amend the specifications of this product at any time without prior notice to third parties.

